



# 1318-1, 1318-2 Tape

## Polyester Film Tape with Acrylic Pressure-Sensitive Adhesive

### Data Sheet



#### Product Description

3M™ 1318 Tape is a polyester film tape with acrylic pressure-sensitive adhesive. It has excellent flagging resistance and solvent resistance, making it well suited for applications where cleaning solvents and mineral oil are present. It consists of materials that are represented in many UL Recognized Insulation Systems and has a UL 130°C temperature rating. It offers good wet grab, excellent shelf life, smooth, even unwind and is suitable for printing.

- UL Recognized Class 130°C
- Excellent Flagging Resistance
- Printable
- Solvent resistant without thermosetting
- Excellent Shelf Life

#### Colors

3M 1318 Tape is available in yellow, white and black.

#### Applications

3M 1318 Tape is especially suited for applications such as wrapping coils, capacitors, wire harnesses, transformers, shaded pole motors and fractional horsepower motors.

#### UL Component Recognition

UL Recognized for use at temperatures not exceeding 130°C. UL File Number E17385, Guide OANZ2. Underwriters Laboratories (UL) Recognized products are evaluated for use as components of end-product equipment that is Listed or Classified by UL. To achieve Underwriters Laboratories Recognition, component construction must meet UL specifications and conditions of acceptability for proper and safe use of the component or products.

| Typical Properties                           | 1-mil Film            | 2-mil Film            |
|--|-----------------------|-----------------------|
| Adhesive                                     | Acrylic               | Acrylic               |
| Backing                                      | Polyester film        | Polyester film        |
| Backing Thickness <sup>1</sup>               | 1.0 mil (25 micron)   | 2.0 mils (50 micron)  |
| Total Thickness                              | 2.5 mils / 0,063 mm   | 3.3 mils / 0,088 mm   |
| Colors-Designation                           | Yellow, White, Black  | Yellow, White, Black  |
| Temperature Class                            | 130°C (266°F)         | 130°C (266°F)         |
| Dielectric Breakdown <sup>1</sup>            | 5,500 Volts           | 7,000 Volts           |
| Insulation Resistance <sup>1</sup> (megohms) | >1 x 10 <sup>6</sup>  | >1 x 10 <sup>6</sup>  |
| Breaking Strength <sup>1</sup>               | 25 lbs./in (44N/10mm) | 50 lbs./in (88N/10mm) |
| Elongation <sup>1</sup> (% at break)         | 100                   | 110                   |
| Electrolytic Corrosion Factor <sup>2</sup>   | 1.0                   | 1.0                   |
| Adhesion to Steel <sup>1</sup>               | 30 oz/in (3,3N/10mm)  | 30 oz/in (3,3N/10mm)  |
| Printable                                    | Yes                   | Yes                   |
| CTI Material Group                           | I                     | I                     |

**Note:** Typical properties are not recommended for specification purposes. Product specifications will be provided upon request.

Footnote: 1 Test Method ASTM D 1000

2 UL-recognized for flame retardancy per UL510, Product Category OANZ2, File E17385

3M is a trademark of 3M

**IMPORTANT NOTICE**

Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

**Warranty; Limited Remedy; Limited Liability.** This product will be free from defects in material and manufacture as of the date of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether direct, indirect, special, incidental or consequential regardless of the legal theory asserted.**



**Electrical Products Division**

6801 River Place Blvd.  
Austin, TX 78726-9000  
<http://www.3M.com/elpd/oem>

Litho in USA.  
© 3M IPC 2001 78-8124-4749-4-B